



---

## Plastic Pigments – Starkemicals

---

TYPE	COLOUR	CODE	COL CODE	C.I.	Heat Resistance (°C)	Density (g/cm3)	Migration Resistance	Full tone	Tint tone	PE	PP	PVC	PS	PMMA	PC	PET	ABS	PA	POM	RUBBER	REMARK
SKP	BROWN	25BR25	PBR	25	290	1,5	4-5	8	8	X	X	X		X					X	X	
SKP	BROWN	25BR41	PBR	41	300	1,6	4	8	8	X	X	X	X	X			O		X	X	
SKP	ORANGE	4O13	PO	13	200	1,5	3-4	5	3-4		X	O								O	
SKP	ORANGE	22O64	PO	64	300	1,5	5	7-8	7-8	X	X	X	X	O			X		X	X	
SKP	RED	25R144	PR	144	300	1,5	5	8	7-8	X	X	X	X	X	O		X		X	X	OK PP fibers
SKP	RED	26R149F	PR	149	300	1,6	5	8	7	X	X	X	X	O	X	X	X	X	O	X	OK PA fibers
SKP	RED	25R166	PR	166	300	1,5	5	8	7	X	X	X	X	O			O		X	X	OK PP fibers
SKP	RED	25R175	PR	176	260	1,4	5	7	6-7	X	X	X		X	X					X	
SKP	RED	25R185	PR	185	250	1,5	5	7-8	7	X	X	X	X							X	
SKP	RED	25R208	PR	208	250	1,4	4-5	7	6-7	X	X	X								X	
SKP	RED	25R214	PR	214	300	1,5	5	8	7-8	X	X	X	X	X	X	X	X		X	X	OK PP PET fibers
SKP	RED	25R242	PR	242	300	1,6	5	8	7-8	X	X	X	X	X	X	X	X		X	X	
SKP	YELLOW	4Y17	PY	17	200	1,5	3	7	6-7	X	X	X	O							X	
SKP	YELLOW	25Y93	PY	93	280	2	5	7-8	7	X	X	X	X				O		X	X	OK PP fibers
SKP	YELLOW	25Y95	PY	95	280	1,4	5	8	7-8	X	X	X	X	O			O		X	X	
SKP	YELLOW	25Y128	PY	128	240	1,5	5	8	8	O	O	X	O				O			X	
SKP	YELLOW	22Y138	PY	138	260	1,7	5	8	7				X		X		O				
SKP	YELLOW	25Y139	PY	139	240	1,7	5	8	7	X	O	O	X						O	X	OK PP fibers
SKP	YELLOW	25Y151	PY	151	290	1,5	5	8	8	X	X	X	X				O		X	X	
SKP	YELLOW	25Y155	PY	155	240	1,4	4	7-8	7-8	X	X	X		X					X	X	OK PP fibers
SKP	YELLOW	25Y180 GS	PY	180	290	1,4	5	6-7	6-7	X	X	X	X	X	X		X		X	X	OK PP fibers
SKP	YELLOW	25Y181	PY	181	300	1,5	5	8	8	X	X	X	X	X			X		X	X	
SKP	YELLOW	4Y191	PY	191	300	1,7	3	7-8	6-7	X	X	X									

X	Recommended
O	Suitable
Migration resistance scale: 0-5	
Full tone scale: 0-8	
Tint tone scale: 0-8	